

## ***New & Improved DYNA-PURGE® M*** ***Most versatile & widely used in the Plastics Industry***

**DYNA-PURGE M** is a versatile non-abrasive, non-chemical engineered thermoplastic purging compound, formulated to flow naturally through the barrel and hot runner system of the injection molding machine, as well as extrusion equipment. Two non-melting but softening thermoplastic ingredients scrub, while an exclusive proprietary additive helps to remove any contamination without leaving a residue.

<b>Applications:</b>	<b>Injection</b> - cold and hot runners <b>Extrusion</b> - profile, sheet, compounding & blow molding
<b>Temperature Range:</b>	350° F - 600° F (177° C - 315° C)
<b>Types of Resins:</b>	All
<b>Minimum Clearance:</b>	.030 inch or .75 mm
<b>Amount of Purge:</b>	1 to 2 times barrel capacity(actual amount needed depends on machine conditions)

### **FEATURES & BENEFITS:**

- Developed for color changes, resin changes, preventative machine maintenance and before manual cleaning
- Excellent for purging through hot runner systems with a minimum clearance of .030 inch (.75 mm)
- Effective through a wide temperature range 350°F to 600°F(177°C to 315°C)
- Easy to use – no process adjustment necessary – use at the resident resin processing temperature and RPM speed
- Non-abrasive, non-melting but softening thermoplastic, which thoroughly loosens carbonized and degraded resin, allowing it to be flushed out of the system
- Safe, non-hazardous, with no chemicals – ingredients are FDA compliant
- Heat stable – recommended during shutdown and start-up
- Low “cost-per-purge” – only small quantity needed to be effective
- No mixing required – simply use “as is”
- Unlimited shelf life

Dyna-Purge has been the top performing purging compound for over 30 years! Our product line offers superior cleaning and economic value over in-house methods and other commercial purges. We invite you to sample Dyna-Purge at no charge, so you can prove it to yourself.

***Please refer to “Suggested Purging Procedures” for processing information and “Grade Selection Guide” regarding additional products.***

Important! The information presented herein, while not guaranteed, was prepared by competent technical personnel and is true to the best of our knowledge. NO WARRANTY OR GUARANTY, EXPRESS OR IMPLIED, IS MADE REGARDING PERFORMANCE, SUITABILITY OR OTHERWISE. This information is not intended to be all-inclusive as to the manner and conditions of use, handling or storage. Other factors may involve other or additional safety or performance considerations. While our technical personnel can respond to questions regarding safe handling and use procedures, safe handling and use remains the responsibility of the customer. No suggestions for use are intended as, and nothing herein shall be construed as, a recommendation to infringe any existing patents or to violate any Federal, State or local laws.